

**VARATHANE®
PREMIUM WOOD PUTTY****DESCRIPTION AND USES**

Varathane® Premium Wood Putty is an easy to use, non-hardening wood putty. It is ideal for filling nail holes and minor defects after assembly and finishing.

PRODUCTS

3.75 ounce Jar	Description
223177	Natural
223178	Cherry
223179	Fruitwood
223250	Colonial Maple
223251	Dark Maple
223252	Red Mahogany
223253	Golden Oak
223254	Dark Walnut

PRODUCT APPLICATION**SURFACE PREPARATION**

Surface must be clean and dry. Apply stain, seal or topcoat the surface before applying the putty. Allow any previously applied oil or stain on wood surface to dry 72 hours before applying Wood Putty. If sanding the surrounding area is needed, sand using 150-220 grit sandpaper and remove all sanding dust with a vacuum or a rag dampened with mineral spirits

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)**APPLICATION**

Press putty into nail hole or other imperfections. Wipe excess putty from the surrounding area using a plastic putty knife or a damp cloth. The putty will NOT harden to a sandable surface. Colors can be blended for custom matches.

Caution: May cause skin irritation. Wash with soap and water to remove from skin.

CLEAN UP

Clean up with soap and water.

**TECHNICAL DATA****VARATHANE® PREMIUM WOOD PUTTY**

		Premium Wood Putty
Resin Type		Acrylic
Pigment Type		Inorganic and Silica
Solvents		Water
Weight	Per Gallon	14.0-15.4 lbs.
	Per Liter	1.69-1.85 kg
Solids	By Weight	71.2-77.1%
	By Volume	51.4-58.0%
Volatile Organic Compounds		<60 g/l
Recommended Dry Film Thickness (DFT) Per Coat		NA
Wet Film to Achieve DFT (unthinned material)		NA
Theoretical Coverage at 1 mil DFT (25µ)		50-58 sq.ft./pint
Practical Coverage at Recommended DFT (assumes 15% material loss) for 6 oz tube		Varies with type and porosity of wood
Dry Times at 77°F (25°C) and 50% Relative Humidity	Touch	1 hour
	Handle	1-2 hours
Shelf Life		3 years
Flash Point		>200°F (93°C)
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.